

CYS-E7628 FABRIC

CYS-E7628 GLASS FABRICS used for printed boards are manufactured with advanced technologies and modern equipment. They are especially designed for printed boards. It has excellent properties of electrical insulation and processing. They are the necessary basic materials for electronic industry such as computers and communication equipments.

Product Features

- ★ Even fabric thickness
- ★ Excellent wet out with resin
- ★ Excellent electrical insulating property
- ★ Very few appearance defects
- ★ Excellent process performance



Technical Parameters

Product Code	CYS-E7628	
Thickness (mm)	0.2±0.02	
Width (mm)	1270±10	
Weight (g/m ²)	200±10	
Diameter roll (cm)	longitude	17.4±1
	latitude	12.2±1
Strength (N/25*100mm)	longitude	≥800
	latitude	≥590
Roll length (m)	400-2400	

Packaging

The product can be packed into Rolls or Pallet.

Roll Length (m)	400~2400
Roll No. per Pallet	1~4
Pallet Size (mm)	1140x1140x1100
Pallet Net Weight (kg)	600~762



Storage

E glass 7628 fabric should be stored in its original packing in a dry, cool and water-proof place. The recommended condition are at temperatures from 15 to 35°C and humidity between 35 and 65%. To ensure safety and avoid damage to the product, the pallets should not be stacked more than three layers high, when the pallets are stacked in 2 or 3 layer, care should be taken to correctly and smoothly move the top pallet.



Tel: +86-28-84400953
Fax: +86-28-84528597
Cell phone: +86-13908045028

Email: liyibin@169chem.net info@169chem.net
MSN: liyibinle@hotmail.com info@169chem.net
http: //www.169chem.net



CYS-E 7628印制电路板用处理玻纤布

印制电路板用处理玻纤布采用先进技术与装备生产，具有优良的电绝缘性能和加工性能。主要应用于印制电路板，是电子计算机以及通讯设备等电子工业中不可缺少的基础材料。

产品特性

- ★ 厚薄均匀
- ★ 树脂浸透性能好
- ★ 电绝缘性能优良
- ★ 外观疵点少
- ★ 优良的加工性能



技术参数

产品编号	CYS-E7628	
厚度 (mm)	0.2±0.02	
幅宽 (mm)	1270±10	
重量 (g/m ²)	200±10	
密度 (cm)	longitude	17.4±1
	latitude	12.2±1
抗拉强度 (N/25*100mm)	longitude	≥800
	latitude	≥590
卷长 (m)	400-2400	

包装

7628布成卷用塑料薄膜包装，外用纸箱及托盘包装

卷长 (m)	400~2400
每拖卷数	1~4
托盘规格 (mm)	1140x1140x1100
净重 (kg)	600~762



应用



存储

如果没有特殊要求，该玻纤布应存放在凉爽干燥的环境中，为防止受潮，请在使用前不要打开包装。



电话: +86-28-84400953
传真: +86-28-84528597
手机: +86-13908045028

邮箱: liyibin@169chem.net info@169chem.net
MSN: liyibinle@hotmail.com info@169chem.net
网址: //www.169chem.net

