

CYS-HS54R High Silica Twist Wick for E-cigs

CYS-HS54R High Silica Twist Wick for E-cigs is specially produced for E-cigarette atomizer. It is twisted of special glass fiber yarn into rope and sintered at high temperatures. It can be worked above 1000°C for long-term and melting point 1700°C. It is characterized by good oil absorption, high temperature resistance, no toxic, no odor, long life working, etc.



Product Features

- ★ High oil absorption
- ★ Quick oil guide
- ★ No odor
- ★ High temperature resistance
- ★ Low fuzz
- ★ Uniform thickness
- ★ No harm to human body

Meet the 6 test requirements in ROHS

Type of glass	High silica
Product code	CYS-HS54R
Diameter (mm)	0.5~3.5
Linear Density (tex)	350~4800

Application

Especially for E-cigarette atomizer. It can also be used in hair drier and electric oven, etc.

Technical Parameters

Content of SiO ₂	Linear Density	Diameter	High temperature shrinkage rate	Structure
> 96%	± 5%	± 10%	< 4%	Twist


Storage

High Silica Twist Wick should be stored in its original packaging in a dry and cool place. Best Conditions are at temperatures from 15 to 35°C and humidity between 35 and 65%. To ensure safety and avoid damage to the product.

Packaging

The product can be packed on paper tube.

Coil height (mm)	245
Tube bottom diameter (mm)	40
Tube top diameter (mm)	27
Package weight (kg)	0.5~1.0
Number of layers	1
Number of coils per layer	25, 30
Net weight per carton (kg)	15~25
Carton length (mm)	540
Carton width (mm)	460
Carton height (mm)	280



Tel: +86-28-84400953
Fax: +86-28-84528597
Cell phone: +86-13908045028

Email: liyibin@169chem.net info@169chem.net
MSN: liyibinle@hotmail.com info@169chem.net
http: //www.169chem.net



CYS-HS54R电子烟专用纤维加捻绳

CYS-HS54R电子烟专用纤维加捻绳是专为电子烟配件、雾化器生产的材料，它由特种纤维经加捻、高温烧结而成。可在1000°C高温长期工作，软化点接近1700°C。具有优良的吸油性，耐高温，无毒，无异味，使用寿命长，等特性。



产品特性

- ★ 吸油性好
- ★ 快速导油
- ★ 无异味
- ★ 耐高温
- ★ 无毛羽
- ★ 粗细均匀
- ★ 对人体无害

满足ROHS 6项测试要求

产品型号	CYS-HS54R
当量直径 (mm)	0.5~3.5
线密度 (tex)	350~4800

应用

专用于电子烟配件、雾化器等，也可以用于保险丝，电吹风、暖风机等电热电器的阻丝的紧固绑扎耐压耐温管的绝缘补强材料。

技术参数

SiO ₂ 含量	线密度	直径	热收缩率	结构
≥96%	±5%	±10%	<4%	加捻


存储

在没有特殊要求的情况下，电子烟专用纤维加捻绳应贮存在干燥、凉爽的地方，防止受潮，产品在使用前应始终保存在原包装内。建议保持室内温度平衡，最佳贮存条件为15~35°C，湿度35~65%。为确保安全，避免损坏产品，托盘的堆码高度不应超过三层。当堆放两层或三层高时，要求正确地、平稳地移动上面的托盘。

包装

该产品缠绕于纸管上，纸箱包装。

卷高 (mm)	245
纸管底部直径 (mm)	40
纸管顶端直径 (mm)	27
包装重量 (kg)	0.5~1.0
包装层数	1
每层卷数	25, 30
每箱净重 (kg)	15~25
纸箱长度 (mm)	540
纸箱宽度 (mm)	460
纸箱高度 (mm)	280



电话: +86-28-84400953
传真: +86-28-84528597
手机: +86-13908045028

邮箱: liyibin@169chem.net info@169chem.net
MSN: liyibinle@hotmail.com info@169chem.net
网址: //www.169chem.net

